

Q1  
Sub  
D2  
12. (twice amended) A tube according to claim 10, wherein the inner seal layer is selected from the group consisting of polypropylene and polyethylene, and mixtures thereof.

13. (twice amended) A tube according to claim 10, wherein the outside layer is selected from the group consisting of polyethylene terephthalate and polyethylene naphthalate.

C2  
Sub  
D4  
15. (twice amended) A tube according to claim 14, wherein the barrier layer comprises aluminum and has a thickness of 7-12 microns.

16. (twice amended) A tube according to claim 14, wherein the barrier layer comprises para-aramide.

VERSION WITH MARKINGS TO SHOW CHANGES MADE

12. A tube according to claim 10, wherein the inner seal layer [consists of] is selected from the group consisting of polypropylene and[/or] polyethylene, and mixtures thereof.

13. A tube according to claim 10, wherein the outside layer [consists of] is selected from the group consisting of polyethylene terephthalate and[/or] polyethylene naphthalate, and mixtures thereof.

15. A tube according to claim 14, wherein the barrier layer [consists of] comprises aluminum and has a thickness of 7-12 microns.

16. A tube according to claim 14, wherein the barrier layer [consists of] comprises para-aramide.